

October, 2017

3M™ High Strength Double Coated Tape 93010LE

Product Description

Finite Element Analysis (FEA) data is available for this product at: 3m.com/FEA

3M™ Double Coated Tapes with 3M™ High Strength Acrylic Adhesive 300LSE provides a high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints. The acrylic adhesive also provides excellent adhesion to surfaces contaminated with oil typically used with machine parts.

Product Features

- This tape has a film carrier which can add dimensional stability to foams and other substrates and also makes it easier to handle the tape during slitting and die-cutting.
- The bond strength of 3M™ Acrylic Adhesive 300LSE increases as a function of time and temperature, and has very high initial adhesion.



3M™ High Strength Double Coated Tape 93010LE

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Notes
Total Tape Thickness without liner	0.10 mm	3.9 mil	
Faceside Adhesive Thickness	0.044 mm	1.7 mil	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Backside Adhesive Thickness	0.044 mm	1.7 mil	Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Carrier Thickness	0.012 mm	0.5 mil	
Faceside Adhesive Type	300LSE		Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Backside Adhesive Type	300LSE		Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Adhesive Carrier	Clear Polyester		
Liner	58# Polycoated Kraft		
Liner Thickness	0.10 mm	4.0 mil	The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.
Liner Color	Tan		

Typical Performance Characteristics

Relative High Temperature Operating Ranges		Test Condition
149 °C	300 °F	Short Term (minutes, hours)
121 °C	250 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

Typical Performance Characteristics (continued)

180° Peel Adhesion		Dwell/Cure Time	Substrate
9.3 N/cm	85 oz/in	15 min @ Room Temperature	Stainless Steel
12.3 N/cm	110 oz/in	15 min @ Room Temperature	Polycarbonate (PC)
8.8 N/cm	80 oz/in	15 min @ Room Temperature	ABS
10.4 N/cm	95 oz/in	15 min @ Room Temperature	Polypropylene (PP)
12.0 N/cm	110 oz/in	72 hr @ Room Temperature	Stainless Steel
15.3 N/cm	140 oz/in	72 hr @ Room Temperature	Polycarbonate (PC)
12.0 N/cm	110 oz/in	72 hr @ Room Temperature	ABS
12.0 N/cm	110 oz/in	72 hr @ Room Temperature	Polypropylene (PP)

Property: 180° Peel Adhesion
 Method: ASTM D3330
 Backing: Aluminum Foil

Property	Values	Method	Test Condition	Notes
Static Shear	>10,000 min	ASTM D3654	1000 g @ Room Temperature	1 in ² sample size
Static Shear	>10,000 min	ASTM D3654	500 g @ 70°C (158°F)	1 in ² sample size

Available Sizes

Property	Values	
Note	Subject to Minimum Order Requirements	
Normal Slitting Tolerance	± 0.8 mm	± 1/32 in
Core Size (ID)	76.2 mm	3 in

Maximum Length		Width
164 m	180 yd	1/2 in to 63/64 in
329 m	360 yd	1 in to 3 in
329 m	360 yd	3 in to 48 in
329 m	360 yd	48 in to 54 in

Property: Maximum Length

Electrical and Thermal Properties

Property	Values
Breakdown Voltage	5600 V
Dielectric Strength	1400 V/mil

Environmental Performance

Humidity Resistance: High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance: When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

Water Resistance: Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

Temperature Cycling Resistance: High bond strength is maintained after cycling four times through:

4 hours at 158°F (70°C)

4 hours at -20°F (-29°C)

4 hours at 73°F (22°C)

Chemical Resistance: When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids, and alkalis.

Handling/Application Information

Application Ideas

- Foam to powder coated painted surfaces.
- Low surface energy plastic adhesion.

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*

*Note: Carefully read and follow the manufacturer's precautions and directions for use when using solvents. Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Storage and Shelf Life

Store in original cartons at 70°F (21°C) and 50% relative humidity.

If stored under proper conditions, these products retain their performance and properties for 24 months from date of manufacture.

Trademarks

3M is a trademark of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/-/3M-Double-Coated-Tape-93010LE?N=5002385+3293240964&rt=rud

Table continued on next page

3M™ High Strength Double Coated Tape 93010LE

References (continued)

Property	Values
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=93010LE

Family Group

	93010LE	93015LE	93020LE
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	149	149	149
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	121	121	121
Total Tape Thickness without liner (mm)	0.1	0.15	0.2
Faceside Adhesive Thickness (mm)	0.044	0.069	0.095
Backside Adhesive Thickness (mm)	0.044	0.069	0.095
Carrier Thickness (mm)	0.012	0.012	0.012
Faceside Adhesive Type	300LSE	300LSE	300LSE
Backside Adhesive Type	300LSE	300LSE	300LSE
Adhesive Carrier	Clear Polyester	Clear Polyester	Clear Polyester
Liner	58# Polycoated Kraft	58# Polycoated Kraft	58# Polycoated Kraft
Liner Thickness (mm)	0.1	0.11	0.11
Liner Color	Tan	Tan	Tan

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

